



Tel. +41 (0)44 939 18 68  
Fax +41 (0)44 939 18 02  
E-Mail: [info@taxidermy.ch](mailto:info@taxidermy.ch)  
Internet: [www.taxidermy.ch](http://www.taxidermy.ch)  
MWSt-Nr. 463 718  
PC 80-133264-3

## Quality

*Conservation board natural white, multiple ply (thicknesses: 1.5/2.0/2.5 mm)*

- 100% bleached cellulose
- without the usage of recycling fibres
- free of wooden fibres
- Kappa level 1 – 2 = lignin-free
- pH 7.5 - 10.0 = acid-free (in accordance with ISO 6588-1:2020)
- alkaline buffer > 3% natural calcium carbonate (GCC)
- sizing: neutral/synthetic (without alum additive)
- without optical brightening agents
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

## Glue used for lamination

- emission-free starch-based adhesive (based on potato starch)
- free of softeners and plasticizers
- VOCs-free
- free of solvents and softening agents
- pH approx. 7.0
- ageing-resistant (permanent)
- Photographic Activity Test (PAT) passed in accordance with ISO 18916:2007

**This quality corresponds to the technological basis of the following standards:**

- DIN EN ISO 9706 Information and documentation – Paper for documents – Requirements for permanence
- ANSI/ NISO Z.39.48 American National Standard for Permanence of Paper for Publications and Documents in Libraries and Archives
- DIN 6738:2007 Highest level of permanency LDK 24-85